



IRAN REFRACTORIES COMPANY

TECHNICAL DATA SHEET



ALMA 80

Classification:	High Alumina Brick
Main Raw Material Component:	Bauxite (Rotary Kiln)
Type Of Bond:	Ceramic
P.C.E. (Equivalent temperature)	> 36 (1804°C)
Main Applications:	Various purposes; Working & Safety layers in steel melting vessels, EAF roof, Rolling mill plants & high temp. zones of cement plants as well as Chemical & Nonferrous Industries, Excellent resistance to high temperature.

Chemical Composition (Calcined base)			
Al ₂ O ₃ %	SiO ₂ %	Fe ₂ O ₃ %	TiO ₂ %
78 – 81	12 – 14	2.0 – 3.0	3.0 – 4.0

Physical Properties		
Bulk Density	g/cm ³	> 2.50
Cold Crushing Strength	kg/cm ²	> 550
Apparent Porosity	%	< 19
Modulus of Rupture	kg/cm ²	> 80

Thermomechanical Properties		
Refractoriness under Load T05	°C	Min 1500
Reversible Linear thermal expansion (1300 °C)	%	≈ 1.0

The above data are typical of the properties of commercial Standard brick .

The data are subject to reasonable variation and therefore should not be used for Specification purposes. They may not be regarded as committed specifications and therefore not as guaranteed properties .

ASTM Test Methods, where applicable, used for determination of data.

Revision:6

Date of issue: 1397/08/15

Code: IRF-ST-Q-860-19

Revision:00