



IRAN REFRACTORIES COMPANY

TECHNICAL DATA SHEET



IRECAST H

Temperature Service:	1550 °C
Classification:	Medium Alumina castable
Main Raw Material Component:	Super duty chamotte & calcium – aluminate binder
Type Of Bond:	Hydraulic
Grain Size:	0 – 5 mm
Water required For Pouring:	9 – 11 %
Dry Castable Required:	2250 Kg/m ³
Features and Main Applications:	Developed for use in extreme abrasion applications in equipment such as cyclones & piping, materials handling equipment, rotary kilns & etc. Excellent strength throughout its temperature range. Adaptable for gunning, casting, or troweling. Highly abrasion resistant. Must be pre dampened before gunning .

Chemical Composition (Calcined base)				
Al₂O₃ %	SiO₂ %	Fe₂O₃ %	CaO %	TiO₂ %
50-54	38-40	1.4-1.8	4.0-6.0	1.2-2.0

Thermomechanical Properties			
		<i>After drying at 110 °C</i>	<i>After heating at 1480 °C</i>
Bulk Density	(Kg/m ³)	> 2290	–
Cold Crushing Strength	(kg/cm ²)	300-600	500-800
Modulus of Rupture	(kg/cm ²)	60-120	60-120
Linear Change	(%)	Negligible	– 0.8 to + 0.5

All data based on cast specimens . ASTM procedures , where applicable , used for determination of data .

For data of vibration cast or gunned , consult our sales & Engineering service's experts .

All data subject to reasonable deviations , and therefore , should not be used for specification purposes. ASTM Test Methods, where applicable, used for determination of data.

Revision:3

Date of issue: 1397/09/05

Code: IRF-ST-Q-860-19

Revision:00