



# IRAN REFRACTORIES COMPANY

## TECHNICAL DATA SHEET



### IREFCAST H LC50

<b>Temperature Service:</b>	1540 °C
<b>Classification:</b>	Medium Alumina, Low cement castable
<b>Main Raw Material Component:</b>	Super duty chamotte & calcium – aluminate binder
<b>Type Of Bond:</b>	Hydraulic
<b>Water required For Pouring</b>	9 – 11 %
<b>Dry Castable Required</b>	2200 Kg/m <sup>3</sup>
<b>Features and Main Applications:</b>	Has excellent consistency and flow ability for would casting operating. Developed for use in extreme abrasion applications in equipment such as cyclones & piping , materials handling equipment , rotary kilns & etc.

<b>Chemical Composition</b> (Calcined base)				
<b>Al<sub>2</sub>O<sub>3</sub> %</b>	<b>SiO<sub>2</sub> %</b>	<b>TiO<sub>2</sub> %</b>	<b>Fe<sub>2</sub>O<sub>3</sub> %</b>	<b>CaO %</b>
>50	<40	<3	<2	<5

<b>Thermomechanical Properties</b>			
		<i>After drying at 110 °C</i>	<i>After heating at 1480 °C</i>
<b>Bulk Density</b>	(Kg/m <sup>3</sup> )	> 2290	–
<b>Cold Crushing Strength</b>	( kg/cm <sup>2</sup> )	400-600	550-750
<b>Modulus of Rupture</b>	( kg/cm <sup>2</sup> )	80-140	60-90
<b>Linear Change</b>	( %)	Negligible	– 0.8 to + 0.5

All data based on cast specimens . ASTM procedures , where applicable , used for determination of data .

For data of vibration cast or gunned , consult our sales & Engineering service's experts .

All data subject to reasonable deviations , and therefore , should not be used for specification purposes. ASTM Test Methods, where applicable, used for determination of data.

Revision:1

Date of issue: 1397/09/05

Code: IRF-ST-Q-860-19

Revision:00