



# IRAN REFRACTORIES COMPANY

## TECHNICAL DATA SHEET



### IREFGUN 29

<b>Temperature Service:</b>	1650 °C
<b>Classification:</b>	High Alumina Gunning mix
<b>Main Raw Material Component:</b>	Blended mixture of carefully sized Bauxite and low Iron calcium aluminate binder .
<b>Type Of Bond:</b>	Hydraulic
<b>Grain Size</b>	0 – 4 mm
<b>Features and Main Applications:</b>	Developed for use in extreme abrasion applications in equipment such as cyclones & piping, materials handling equipment, rotary kilns & etc. Highly abrasion resistant. Excellent strength throughout its temperature range and thermal shock resistance. Adaptable for gunning, or troweling. Must be pre dampened before gunning .

<b>Chemical Composition</b> (Calcined base)			
<b>Al<sub>2</sub>O<sub>3</sub> %</b>	<b>SiO<sub>2</sub> %</b>	<b>Fe<sub>2</sub>O<sub>3</sub> %</b>	<b>CaO %</b>
58 – 61	28 – 30	1.5 – 2.5	4.5 – 6.5

  

<b>Thermomechanical Properties</b>			
		<i>After drying at 110 °C</i>	<i>After heating at 1480 °C</i>
<b>Bulk Density</b>	(Kg/m <sup>3</sup> )	> 2400	–
<b>Cold Crushing Strength</b>	( kg/cm <sup>2</sup> )	400-600	500-800
<b>Modulus of Rupture</b>	( kg/cm <sup>2</sup> )	60-100	70-100
<b>Linear Change</b>	( %)	Negligible	– 1.5 to + 0.5

All data based on cast specimens . ASTM procedures ,where applicable, used for determination of data .

For data of vibration cast or gunned , consult our sales & Engineering service's experts .

All data subject to reasonable deviations , and therefore , should not be used for specification purposes. ASTM Test Methods, where applicable, used for determination of data.

Revision:1

Date of issue: 1397/09/05

Code: IRF-ST-Q-860-19

Revision:00