



IRAN REFRACTORIES COMPANY

TECHNICAL DATA SHEET



MAGNAMI 95 HR

Temperature Service:	1750 °C
Classification:	Dry Repair mix made from dead burned magnesite.
Main Raw Material Component:	Dead Burned Magnesia
Type Of Bond:	Ceramic
Grain Size:	0 – 8 mm
Dry Material Required:	2700 Kg/m ³
Features and Main Applications:	Repair mix, Contains high grade dead-burned magnesite with added oil, with special grain structure, for bank of electric arc furnaces. Highly recommended whenever quick setting is required.

Chemical Composition (Calcined base)				
MgO %	Fe ₂ O ₃ %	CaO %	SiO ₂ %	Al ₂ O ₃ %
91.5	1.1	1.9	3.5	0.3

Thermomechanical Properties		
<i>After drying at 110 °C</i>		
Bulk Density	(Kg/m ³)	> 2700

All data based on cast specimens. ASTM procedures, where applicable, used for determination of data.

For data of vibration cast or gunned, consult our sales & Engineering service's experts.

All data subject to reasonable deviations, and therefore, should not be used for specification purposes. ASTM Test Methods, where applicable, used for determination of data.

Revision:3

Date of issue: 1397/09/05

Code: IRF-ST-Q-860-19

Revision:00