



MAGNOGUN EA

Temperature Service:	1750 °C
Classification:	Gunning mix made from dead burned magnesite
Main Raw Material Component:	Dead Burned Magnesia
Type Of Bond:	Chemical Bonded
Grain Size	0 – 3 mm
Features and Main Applications:	High quality gunning mix with excellent prime adherence for converters and electric arc furnaces and steel-ladles.

Chemical Composition (Calcined base)				
MgO %	Fe ₂ O ₃ %	CaO %	SiO ₂ %	Al ₂ O ₃ %
84 – 86	2.5 – 3.5	2.0 – 3.0	7.0 – 9.0	1.0 – 1.5

Thermomechanical Properties		
<i>After drying at 110 °C</i>		
Bulk Density	(Kg/m ³)	> 2100

All data based on cast specimens. ASTM procedures, where applicable, used for determination of data.

For data of vibration cast or gunned, consult our sales & Engineering service's experts.

All data subject to reasonable deviations, and therefore, should not be used for specification purposes. ASTM Test Methods, where applicable, used for determination of data.

Revision:4

Date of issue: 1397/09/05

Code: IRF-ST-Q-860-19

Revision:00