



IRECAST 20 LIS

Max. Temperature Service:	1170 °C
Classification:	Light weight cast able
Main Raw Material Component:	High quality Low Iron chamotte & calcium – aluminate binder
Type Of Bond:	Hydraulic
Grain Size:	0 – 3.6 mm
Water required For Pouring:	45 – 55 %
Dry Castable Required:	860 Kg/m ³
Features and Main Applications:	Low Thermal Conductivity. Good refractoriness, Good strength, Excellent resistance to thermal shock, Stable withstand CO and alkali atmospheres. Easily installed by casting or troweling & may be gunned. Recommended for Chemical & Petrochemical Industries, Various industrial furnaces , boilers , incinerators , stacks and as backup for other refractories suitable for greater mechanical abuse and higher temperatures.

Chemical Composition (Calcined base)			
Al₂O₃ %	SiO₂ %	Fe₂O₃ %	CaO %
33 – 38	40 – 45	< 1.7	10 – 16

Thermomechanical Properties		
		<i>After drying at 110 °C</i>
Bulk Density	(Kg/m ³)	< 920
Cold Crushing Strength	(kg/cm ²)	> 10
Linear Change	(%)	Negligible

All data based on cast specimens . ASTM procedures , where applicable , used for determination of data .

For data of vibration cast or gunned , consult our sales & Engineering service's experts .

All data subject to reasonable deviations , and therefore , should not be used for specification purposes .ASTM

Test Methods, where applicable, used for determination of data.

Revision:3

Date of issue: 1397/09/05

Code: IRF-ST-Q-860-19

Revision:00