



IREFGUN 20 LI

Max. Temperature Service:	1160 °C
Classification:	Ultra Light weight Gunning mix.
Main Raw Material Component:	High quality Low Iron chamotte & calcium-aluminate binder
Type Of Bond:	Hydraulic
Grain Size:	0-3.5 mm
Water required For Pouring:	45 – 55 %
Features and Main Applications:	Low Thermal Conductivity. Excellent resistance to thermal shock, Stable withstand CO and alkali atmospheres. Easily installed by gunning or troweling. Wherever reduction resistance required; particularly in Iron ore pelletizing plants and Petrochemical Industries, Various industrial furnaces, incinerators, stacks and as backup for other refractories. Fast erection insulate backup

Chemical Composition (Calcined base)			
Al₂O₃ %	SiO₂ %	Fe₂O₃ %	CaO %
31 – 38	38-45	<2.0	10 – 16

Thermomechanical Properties		
		<i>After drying at 110 °C</i>
Bulk Density	(Kg/m ³)	< 900
Cold Crushing Strength	(kg/cm ²)	> 10
Linear Change	(%)	Negligible

All data based on cast specimens . ASTM procedures , where applicable , used for determination of data .

For data of vibration cast or gunned , consult our sales & Engineering service's experts .

All data subject to reasonable deviations , and therefore , should not be used for specification purposes .ASTM Test Methods, where applicable, used for determination of data.

Revision:3

Date of issue: 1397/09/05

Code: IRF-ST-Q-860-19

Revision:00