



### IREFGUN 22 LI

<b>Max. Temperature Service:</b>	1230 °C
<b>Classification:</b>	Ultra Light weight Gunning mix.
<b>Main Raw Material Component:</b>	Blended gunable employing Low Iron calcined clays, firm lightweight aggregates & calcium-aluminate binder
<b>Type Of Bond:</b>	Hydraulic
<b>Grain Size</b>	0 – 3.5 mm
<b>Water required For Pouring</b>	44 – 53 %
<b>Features and Main Applications:</b>	Low Thermal Conductivity. Excellent resistance to thermal shock, Stable withstand CO and alkali atmospheres. Easily installed by gunning or troweling. Recommended for Chemical & Petrochemical Industries, particularly in Iron ore pelletizing plants, Various industrial furnaces, incinerators, stacks and as backup for other refractories. Fast erection insulate backup.

<b>Chemical Composition</b> (Calcined base)			
<b>Al<sub>2</sub>O<sub>3</sub> %</b>	<b>SiO<sub>2</sub> %</b>	<b>Fe<sub>2</sub>O<sub>3</sub> %</b>	<b>CaO %</b>
33 – 38	42 – 50	1.3 – 1.6	8 – 12

<b>Thermomechanical Properties</b>			
		<i>After drying at 110 °C</i>	<i>After heating at 1150 °C</i>
<b>Bulk Density</b>	(Kg/m <sup>3</sup> )	< 1100	–
<b>Cold Crushing Strength</b>	( kg/cm <sup>2</sup> )	> 20	> 20
<b>Modulus of Rupture</b>	( kg/cm <sup>2</sup> )	12-35	5-10
<b>Linear Change</b>	( %)	Negligible	– 0.5 to + 0.1

All data based on cast specimens . ASTM procedures , where applicable , used for determination of data .

For data of vibration cast or gunned , consult our sales & Engineering service's experts .

All data subject to reasonable deviations , and therefore , should not be used for specification purposes .ASTM Test Methods, where applicable, used for determination of data.

Revision:2

Date of issue: 1397/09/05

Code: IRF-ST-Q-860-19

Revision:00