



### IREFGUN 23 ESLIS

<b>Max. Temperature Service:</b>	1300 °C
<b>Classification:</b>	Light weight Gunning mix.
<b>Main Raw Material Component:</b>	Blended gunable employing Low Iron calcined clays , firm lightweight aggregates & calcium – aluminate binder
<b>Type Of Bond:</b>	Hydraulic
<b>Grain Size:</b>	0–5 mm
<b>Water required For Pouring</b>	29 – 36 %
<b>Features and Main Applications:</b>	resistance to thermal shock, Stable withstand CO and alkali atmospheres. Easily installed by gunning or troweling. Recommended for Chemical & Petrochemical Industries, particularly in Iron ore pelletizing plants, Various industrial furnaces, incinerators, stacks and as backup for other refractories. Combines good strength with high insulating value. Fast erection insulate backup.

<b>Chemical Composition</b> (Calcined base)			
<b>Al<sub>2</sub>O<sub>3</sub> %</b>	<b>SiO<sub>2</sub> %</b>	<b>Fe<sub>2</sub>O<sub>3</sub> %</b>	<b>CaO %</b>
32 – 38	36 – 40	<1.5	9 – 13

<b>Thermomechanical Properties</b>			
		<i>After drying at 110 °C</i>	<i>After heating at 1200 °C</i>
<b>Bulk Density</b>	(Kg/m <sup>3</sup> )	< 1650	–
<b>Cold Crushing Strength</b>	( kg/cm <sup>2</sup> )	> 20	> 20
<b>Linear Change</b>	( %)	Negligible	– 2.5 to 0.0

All data based on cast specimens. ASTM procedures, where applicable, used for determination of data.

For data of vibration cast or gunned, consult our sales & Engineering service's experts.

All data subject to reasonable deviations, and therefore, should not be used for specification purposes. ASTM Test Methods, where applicable, used for determination of data.

Revision:1

Date of issue: 1397/09/05

Code: IRF-ST-Q-860-19

Revision:00