



IRAN REFRACTORIES COMPANY

TECHNICAL DATA SHEET



ALUMO 70LI

Classification:	Alumina – Mullite Brick
Main Raw Material Component:	Alumina – Mullite
Type Of Bond:	Ceramic
P . C . E . (Equivalent temperature)	> 38 (1835 °C)
Main Application:	Special usages. Petrochemical Industries, Excellent resistance to high temperature, abrasion, corrosion and chemical attacks.

Chemical Composition (Calcined base)				
Al₂O₃ %	SiO₂ %	Fe₂O₃ %	TiO₂ %	Alkalis %
64 – 66	28 – 32	< 1	< 1.5	< 0.5

Physical Properties		
Bulk Density	gr/cm ³	> 2.60
Cold Crushing Strength	kg/cm ²	> 1000
Apparent Porosity	%	< 15
Modulus of Rupture	kg/cm ²	> 100

Thermomechanical Properties		
Refractoriness under Load T05	°C	Min 1540 °C
Reversible Linear thermal expansion (1100 °C)	%	0.6 – 0.9

The above data are typical of the properties of commercial Standard brick .

The data are subject to reasonable Variation and therefore should not be used for Specification purposes . They may not be regarded as committed specifications and therefore Not as guaranteed properties .

ASTM Test Methods, where applicable, used for determination of data.

Revision:00

Date of issue: 1397/08/15

Code: IRF-ST-Q-860-19

Revision:00